

TURBOFIX SR 700

TURBOFIX SR 700 is heavy golden brown viscous liquid of for brushing viscosity. TURBOFIX SR 700 is formulated after intense R&D efforts to address diverse application needs of the industry.

TYPICAL PROPERTIES

- Appearance : Viscous Liquid
- Colour : Golden brown

APPLICATION INSTRUCTIONS

TURBOFIX SR 700 has been developed as multi-purpose high strength adhesive. Forms strong, permanent contact bonds between the following materials ; rigid PVC sheet, polyurethane foams of the polyester and polyester types, supported PVC leather cloth, leather, polyester glass fiber, rubber sheet and extrusions all of which may be bonded to each other or to hardboard, chipboard, wood, painted or unpainted metal. TURBOFIX SR 700 is well established in the automotive and coach building operations. To which TURBOFIX SR 700 is suited include door and fascia trim, roof headlining, parcel racks and glove compartment.

TURBOFIX SR 700 has also proved its versatility in the shop fitting and bar fitting trades and in the boat building, furniture and footwear industries, where they are widely used as multi-purpose adhesives. It has an excellent ageing resistance.

Care should be taken to establish that the backing of the supported PVC leather cloth is of sufficient quality to prevent plasticiser migration.

AREA OF USAGE

METHOD OF USE

- The materials to be bonded should be dry, clean and free of dust, grit, loose materials, oil or grease.
- Using a brush or spreader, apply a thin even coating of adhesive to both the surfaces.
- Allow the solvent content to evaporate before bonding the materials. The time for this evaporation will depend on the temperature and humidity. On absorbent or permeable materials such as leather/chipboard, bonding may be possible within a matter of 2-3 minutes of application; on non-absorbent or non-permeable materials (eg. Formica/metal) a minimum of 15 minutes should elapse before the surfaces are bonded.
- Bond the materials under firm pressure.
- Dried coatings of TURBOFIX SR 700 may be reactivated by wiping over the surfaces with a suitable solvent.

PACKAGING

1 litre, 5 litre, 30 litre & 200 litre

STORAGE AND SHELF LIFE

At least 12 months from date of manufacture in original sealed condition. Low or high temperature storage should be avoided and the adhesive should preferably be stored within the temperature range +5°C upto +35°C.

SERVICES

For further information on this product and application contact Technical Services Department of Nerofix Pvt. Ltd.

IMPORTANT NOTICE

Whilst all reasonable care is taken in the compilation of this data sheet, it is the customer's responsibility to determine the suitability of the product for the desired application.

DISCLAIMER

KANSAI NEROLAC PAINTS LTD. (KNPL) warrants that all products are free from any defects of manufacturing and comply with the specifications given in their respective technical data sheet. No warranty can be given as to the results of use because conditions of use, such as site conditions, surface preparations, workmanship, weather, structural issues and other factors are beyond the control of NEROLAC. Purchaser agrees to seek the advice of qualified professionals to carry-out tests and take trials to determine the suitability of products for their intended purpose, prior to full-scale usage of KNPL products and assumes all risks.

The company does not assume any liability for unsatisfactory results, arising from the use of our products. Purchaser's sole liability is limited to the replacement of the product or refund of the purchase price paid, if any product is proven defective. No other warranties expressed or implied, shall apply including any warranty of merchantability or fitness for any particular purpose.

KNPL shall not be liable for any consequential damages arising from the use of our products for unsatisfactory results.

The information supplied in this data sheet is based on our experience through extensive research and is given in good faith in order to help prospective users. We reserve the right to update the information provided in our technical data sheet at any time without prior notice within the scope of technical progress or new developments.

NEROFIX PRIVATE LIMITED

REGD. OFFICE: 111, THE GREAT EASTERN GALLERIA, PLOT NO. 20, SECTOR -4 NERUL (WEST),
NAVI MUMBAI - 400706, MAHARASHTRA, INDIA

FOR CONSUMER COMPLAINTS AND FEEDBACK, REFER TO THE REGD. OFFICE OF NEROFIX PRIVATE LIMITED OR
CONTACT THE MANAGER, CONSUMER CARE CELL AT: 8291715780 OR EMAIL TO: customercare@nerofixindia.com